



STAPELBARKEIT POLI-FLEX FASHION & IMAGE

STACKING OF POLI-FLEX FASHION & IMAGE

		Down													
Up		Hotstamping	Carbonium	Jeans	Twill	Spangle	Snake	Manta Ray	Marble	Semi Punched Silver	Universal Sports	Starflex	Pearl	Paint	
		Hotstamping	++	++	++	++	++	++	++	++	++	++	--	+	++
		Carbonium	++	++	++	++	++	++	++	++	++	++	--	+	++
		Jeans	++	++	++	++	++	++	++	++	++	++	--	+	++
		Twill	++	++	++	++	++	++	++	++	++	++	--	+	++
		Spangle	++	++	++	++	++	++	++	++	++	++	--	+	++
		Snake	++	++	++	++	++	++	++	++	++	++	--	+	++
		Manta Ray	++	++	++	++	++	++	++	++	++	++	--	+	++
		Marble	++	++	++	++	++	++	++	++	++	++	--	+	++
		Semi Punched Silver	++	++	++	++	++	++	++	++	++	++	--	+	++
		Universal Sports	++	++	++	++	++	++	++	++	++	++	--	+	++
		Starflex	++	0	0	0	0	0	0	0	0	0	--	--	0
		Pearl	++	0	0	0	0	0	0	0	0	0	--	0	0
		Paint	++	++	++	++	++	++	++	++	++	++	--	+	++
		Camouflage	++	++	++	++	++	++	++	++	++	++	--	+	++
	Zebra	++	++	++	++	++	++	++	++	++	++	--	+	++	

Die Materialien wurden entsprechend ihren jeweiligen Transferbedingungen verpresst, 24h bei Raumtemperatur gelagert und anschließend 8* bei 40°C gewaschen.
The materials were pressed according to the specified temperatures, stored 24 hours by room temperature and finally washed at 8 times at 40°.

++: Sehr gute Haftung aufeinander, auch mit Anfasshilfe nicht zu trennen.

+: Materialien haften aufeinander, können mit leichtem Kraftaufwand bzw. Anfasshilfe voneinander getrennt werden. Bedingt zu empfehlen.

0: Materialien haften aufeinander, sind aber voneinander trennbar.

--: Keine Haftung aufeinander.

++: Very good bond when placed on top of each other, does not separate even when handled.

+: Materials bond together when placed on top of each other, can be separated with slight effort, e.g. if pulled apart it can be separated from each other. Only recommended conditionally.

0: Material bond together when placed on top of each other, but with the possibility to separate from each other.

--: No bond when placed on top of each other.